

Technisches Datenblatt/ Technical datasheet

Teichfolie/ Pondliner PVC 1 mm



Produkt Eigenschaften/ Product properties	Spezifikationen/ Specifications	Werte/ Values	Test Methode/ Test Method
Gewicht/ weight		1270g/m ²	DIN 53352
Dicke/ thickness		1mm +/- 8%	DIN 53370
Härte/ hardness		80 +/- 2	DIN 53 505
Dichte/ density		1,36 +/- 0,03g/m ²	DIN 53479
Lackierung/ laquering		-/-	
Reißfestigkeit/ breaking strength	Machine direction Cross direction	>=14N/mm ² >=14N/mm ²	DIN 53455
Bruchdehnung/ Elongation at break	Machine direction Cross direction	>=250% >=250%	DIN 53455
Weitereißfestigkeit/ Tear strength	Machine direction Cross direction	>=80N/mm >=80N/mm	DIN 53363
Maßänderung/ dimensional stability		<=2%	DIN 53 377 6h/80 °C
Kältebeständigkeit/ Cold resistance		-20 °C	DIN 53361
Wurzelfest		Ja /Yes	DIN 4062
Lichtechtheit/ light fastness		500MJ/m ²	DIN EN ISO 4892-3
Anwendung Application	Teichfolie Pondliner		

Heissner GmbH; Schlitzerstraße 24; 36341 Lauterbach

www.heissner.de

info@heissner.de